



**MOSAIC**  
**ANTIQUE**  
**COPPER**  
**FIELDSTONE**

**GEOLOGY:** sandstone

**BASIC USE**

exterior walls of buildings and fireplaces  
stone shall be mortared in

**COLOR RANGE**

burnt tones, browns, buffs, black, red,  
mustard, occasional moss and lichens

**COLOR CONSISTENCY PER PALLET**

somewhat consistent

**WEIGHT CALCULATED IN INCHES**

$l \times w \times h / 1728$  (inches cubed) x 165  
= approx 165 pounds per cubic foot

**PALLET**

FULL VENEER: 3,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)

**FULL VENEER**

**COMMON COVERAGE** \*Est.(can vary)

Standard Joint	Drystack	Overgrout
35 square feet / ton	25 ft <sup>2</sup> /ton	45 ft <sup>2</sup> /ton

**ANTIQUE COPPER FIELDSTONE**

**DIMENSIONS**

**US: inches (average)**    **METRIC: mm (average)**

l: 3" to 16" dia.            l: 76 to 406 dia.

h: 3" to 16" dia.            h: 76 to 406 dia.

w: 3" to 6" (4")            w: 76 to 152 (101)

note: lengths and heights are irregular shapes  
3 inches to 16 inches in diameter

**TYPICAL PIECE**

ends irregular;  
natural split and rounded sides;  
bedface face and back;  
stone is random shapes

**PART NUMBERS**

**FULL VENEER**

part number: 1BSTSCH01002TN

**THIN VENEER**

qty bx flat: 1BTVSCH01001QB

sm bx flat: 1BTVSCH01001BX

qty bx corner: 1BTVSCH01501QB

sm bx corner: 1BTVSCH01501BX

**THIN VENEER**

**COMMON COVERAGE PER BOX** \*Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft <sup>2</sup>	10 & 110 ft <sup>2</sup>

**ANTIQUE COPPER FIELDSTONE**

**DIMENSIONS**

**US: inches (average)**    **METRIC: mm (average)**

l: 3" to 12" dia.            l: 76 to 304 dia.

h: 3" to 12" dia.            h: 76 to 304 dia.

w: 3/4" to 1-1/4" (1")    w: 19 to 31 (25)

corner return 3" to 5"    cr: 76 to 127

note: lengths and heights are irregular shapes  
3 inches to 12 inches in diameter

**TYPICAL PIECE**

ends irregular;  
natural split and rounded sides;  
bedface face and sawn back;  
stone is random shapes

**ASTM TESTING DATA**

**ANTIQUE COPPER C97**

water absorption—2.8%

**ANTIQUE COPPER C97** density—149.3 pcf

**ANTIQUE COPPER C97** specific gravity—2.393

**ANTIQUE COPPER C1549-09**

solar reflectance—24.7%

**ANTIQUE COPPER C1371-15**

thermal emittance—0.90

**ANTIQUE COPPER E1980-11**

solar reflective index—25



www.buechelstone.com