CASTLE ROCK

FULL COLOR CASTLE ROCK



GEOLOGY: dolomitic limestone

BASIC USE

exterior walls of buildings and fireplaces stone shall be mortared in

COLOR RANGE

purple, lavender, mauve, gray, buff, blue, cream and brown

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

I x w x h / 1728 (inches cubed) x 170 = approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds THIN VENEER: 10-15 lbs/ft2; Qty Bx or Sm Bx Qty Bx - 100 sq ft flats and 50 lineal ft corners Sm Bx - (24) 8 sq ft flats (192 sq ft) and (20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint Drystack Overgrout 40 square feet / ton 30 ft²/ton 50 ft²/ton

FULL COLOR CASTLE ROCK

DIMENSIONS _

US: inches (average) METRIC: mm (average) l: 6" to 42" (16") I: 152 to 1066 (406) h: 4" to 12" h: 101 to 304 w: 76 to 127 (101) w: 3" to 5" (4") stone shall not vary in height more than 1/2 an inch in a 12 inch span

a stone that is 24 inches long could have a height of 6 inches on one end and 5 inches on the other end and be acceptable TYPICAL PIECE

ends square: split top, bottom, and sides; bedface face and back; stone is squares and rectangles



PART NUMBERS

FULL VENEER

part number: 1BSTBUE01007TN

THIN VENEER

qty bx flat: 1BTVBUE01006QB sm bx flat: 1BTVBUE01006BX qty bx corner: 1BTVBUE01506QB sm bx corner: 1BTVBUE01506BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint Drystack Overgrout 6 & 75 ft² 10 & 110 ft² 8 & 100 square feet

FULL COLOR CASTLE ROCK

DIMENSIONS __

US: inches (average) METRIC: mm (average) l: 6" to 24" (12") I: 152 to 533 (304) h: 4" to 12" h: 101 to 304 w: 3/4" to 1-1/4" (1") w: 19 to 31 (25) corner return 3" to 5" cr: 76 to 127 stone shall not vary in height more than 1/2 an inch in a 12 inch span

EXAMPLE

a stone that is 24 inches long could have a height of 6 inches on one end and 5 inches on the other end and be acceptable

TYPICAL PIECE

ends square;

split top, bottom, and sides; bedface face and sawn back; stone is squares and rectangles

ASTM TESTING DATA

FULL COLOR C97 water absorption—0.08% FULL COLOR C97 density—177.4 pcf **FULL COLORC99** modulus of rupture-1,220 psi **FULL COLOR C170** compressive strength w/rift-50,560 psi compressive strength across rift-38,090 psi **FULL COLOR C880** flexural strength—3,070 psi

