



## CASTLE ROCK

### ANTIQUÉ COPPER

**GEOLOGY:** sandstone

#### BASIC USE

exterior walls of buildings and fireplaces  
stone shall be mortared in

#### COLOR RANGE

burnt tones, browns, buffs, black, red,  
mustard, occasional moss and lichens

#### COLOR CONSISTENCY PER PALLET

somewhat consistent

#### WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 160  
= approx 160 pounds per cubic foot

#### PALLET

FULL VENEER: 3,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)

## FULL VENEER

### COMMON COVERAGE <sup>\*Est.(can vary)</sup>

Standard Joint	Drystack	Overgrout
35 square feet / ton	25 ft <sup>2</sup> /ton	45 ft <sup>2</sup> /ton

### ANTIQUÉ COPPER

#### DIMENSIONS

US: inches (average)    METRIC: mm (average)

l: 4" to 24" (14")    l: 101 to 609 (355)

h: 4" to 12"    h: 101 to 304

w: 2" to 6" (4")    w: 50 to 152 (101)

#### TYPICAL PIECE

ends somewhat square;  
split or natural split top, bottom, and sides;  
bedface face and back;  
stone is squares and rectangles

## PART NUMBERS

### FULL VENEER

part number: 1BSTSCH02002TN

### THIN VENEER

qty bx flat: 1BTVSCH01003QB

sm bx flat: 1BTVSCH01003BX

qty bx corner: 1BTVSCH01503QB

sm bx corner: 1BTVSCH01503BX

## THIN VENEER

### COMMON COVERAGE PER BOX <sup>\*Est.(can vary)</sup>

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft <sup>2</sup>	10 & 110 ft <sup>2</sup>

### ANTIQUÉ COPPER

#### DIMENSIONS

US: inches (average)    METRIC: mm (average)

l: 4" to 24" (14")    l: 101 to 609 (355)

h: 4" to 12"    h: 101 to 304

w: 3/4" to 1-1/4" (1")    w: 19 to 31 (25)

corner return 3" to 5"    cr: 76 to 127

#### TYPICAL PIECE

ends somewhat square;  
split or natural split top, bottom, and sides;  
bedface face and sawn back;  
stone is squares and rectangles

## ASTM TESTING DATA

### ANTIQUÉ COPPER C97

water absorption—2.8%

ANTIQUÉ COPPER C97 density—149.3 pcf

ANTIQUÉ COPPER C97 specific gravity—2.393

ANTIQUÉ COPPER C1549-09

solar reflectance—24.7%

ANTIQUÉ COPPER C1371-15

thermal emittance—0.90

ANTIQUÉ COPPER E1980-11

solar reflective index—25



www.buechelstone.com