



LEDGESTONE
FOND DU LAC
LEDGESTONE

GEOLOGY: dolomitic limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

gray, light gray,
buff, and white

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) $\times 170$
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

FOND DU LAC LEDGESTONE

DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 4" to 16" (8") l: 100 to 400 (203)

h: 3/4" to 2-1/4" h: 19 to 57

w: 3" to 5" (4") w: 76 to 127 (101)

TYPICAL BLEND

up to 30 percent may be sawn top and
bottom with a bedface face;
face of stone cannot have a sawn finish

TYPICAL PIECE

ends random;
natural cleft top and bottom;
face and sides natural split or seamface;
back sawn; stone is linear

PART NUMBERS

FULL VENEER

part number: 1BSTBUE02044TN

THIN VENEER

qty bx flat: 1BTVBUE02048QB

sm bx flat: 1BTVBUE02048BX

qty bx corner: 1BTVBUE02548QB

sm bx corner: 1BTVBUE02548BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

FOND DU LAC LEDGESTONE

DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 4" to 16" (8") l: 100 to 400 (203)

h: 3/4" to 2-1/4" h: 19 to 57

w: 3/4" to 1-1/4" (1") w: 19 to 38 (25)

corner return 3" to 5" cr: 76 to 127

TYPICAL BLEND

up to 30 percent may be sawn top and
bottom with a bedface face;
face of stone cannot have a sawn finish

TYPICAL PIECE

ends random;
natural cleft top and bottom;
face and sides natural split or seamface;
back sawn; stone is linear

ASTM TESTING DATA

FOND DU LAC C97 water absorption—0.36%

FOND DU LAC C97 density—174.2 pcf

FOND DU LAC C99

modulus of rupture—1,470 psi

FOND DU LAC C170

compressive strength w/rift—29,040 psi

compressive strength across rift—34,240 psi

FOND DU LAC C880

flexural strength—1,740 psi



www.buechelstone.com